

Veralite[®] 200 - Technical data sheet

PHYSICAL PROPERTIES

Properties	Method	Units	Veralite [®] 200
Specific gravity	ISO 1183	g/cm ³	1,27
Water absorption	ISO 62	%	0,15

MECHANICAL PROPERTIES

Properties	Method	Units	Veralite [®] 200
Tensile strength	ISO 527	MPa	51,5
Elongation at break	ISO 527	%	> 100
Tensile modulus	ISO 527	MPa	± 2200
Impact strength unnotched	ISO 180	KJ/m ²	no burst
Impact strength notched	ISO 180	KJ/m ²	9,0
Rockwell hardness	DIN 2039	M / R	M85 / R115

THERMAL PROPERTIES

Properties	Method	Units	Veralite [®] 200
Dilatation coefficient	ASTMD696	mm/mC°	± 0,060
Specific Heat	DSC	J/gC°	1,13
Heat deflection temp. (0,45 MPa)	ISO 75	°C	72
Heat deflection temp. (1,82 MPa)	ISO 75	°C	68
Vicat softening point (1 kg)	ISO 306	°C	82
Vicat softening point (5 kg)	ISO 306	°C	78

OPTICAL PROPERTIES

Properties	Method	Units	Veralite [®] 200
Light transmission	ASTMD1003	%	86 - 90*
Haze	ASTMD1003	%	< 1
Gloss (60° angle)	ASTMD1003	units	159

Veralite® 200 - Technical data sheet

ELECTRICAL PROPERTIES

Properties	Method	Units	Veralite ^o 200
Surface resistivity	ASTMD257	W xcm	1*E15
Dielectric constant	ASTMD150	1 MHz	2,4
Dissipation factor	ASTMD150	1 MHz	0,020
Dielectric strength (500V/sec)	ASTMD149	KV/mm	16
Filament test	IEC 695/2.1	C°	650

BARRIER PROPERTIES

Properties	Method	Units	Veralite ^o 200
Water Vapour	ASTMF372	g/mm/m ² /24h	1,5
Gas permeability for CO ₂	ASTMD1434	g/mm/m ² /24h	49
Gas permeability for O ₂	ASTMD3985	g/mm/m ² /24h	10

Temporary and limited list made to our best knowledge at this time - based upon 3 mm sheet.

The technical data concerning our products are not binding and are given for guidance only.

* Test results from 1 - 3 mm

For more specific information, please feel free to contact our technical department :

I.P.B. nv
Steenovenstraat 30
8790 Waregem
BELGIUM
Tel.+32.56.60.79.19
Fax +32.56.61.08.85